

ROADTEX™ RL 100X100 E17C

Issued : 23.07.08

Revision : 06 from 08.03.18

CONSTRUCTION :		WEIGHT / SQM
Warp	: 0.25 End / cm x 1 x 1200 tex Glass 2 x 2400 tex Glass	300
Scrim	Weft : 0.25 End / cm x 2 x 2400 tex Glass x 2 x 600 tex Glass	
Coating	SBR	83
Tissue	Polyester	17
TOTAL WEIGHT (MO P2000HA-D05)		400 ± 10 %

PROPERTIES : according to ISO 10319			L : length direction T : cross direction
TENSILE STRENGTH	MO 302/63	KN/m	L : > 100 - 5% T : > 100 - 5%
TENSILE STRENGTH AT 1% ELONGATION	MO 302/63	KN/m	L : > 40 - 40% T : > 40 - 40%
TENSILE STRENGTH AT 2% ELONGATION	MO 302/63	KN/m	L : > 80 - 20% T : > 80 - 20%
ELONGATION AT BREAK	MO 302/63	%	L : < 3 + 0,5% T : < 3 + 0,5%
THICKNESS (indicative value)	MO P2000HA-D05	mm	1,4