

**ROADTEX™ RL 50X50 E17B**

Issued : 21.10.08

Revision : 04 from 08.03.18

CONSTRUCTION :		WEIGHT / SQM
Warp	: 0.25 End / cm x 1 x 600 tex Glass 1 x 2400 tex Glass	<b>143</b>
Scrim		
Weft	: 0.25 End / cm x 1 x 2400 tex Glass 1 x 320 tex Glass	
Coating	SBR	<b>46</b>
Tissue	Polyester	<b>17</b>
<b>TOTAL WEIGHT (MO P2000HA-D05)</b>		<b>206 ± 10 %</b>

PROPERTIES : according to ISO 10319			L : length direction T : cross direction
<b>TENSILE STRENGTH</b>	MO 302/63	KN/m	L : > 50 - 5% T : > 50 - 5%
<b>TENSILE STRENGTH AT 1% ELONGATION</b>	MO 302/63	KN/m	L : > 20 - 40 % T : > 20 - 40 %
<b>TENSILE STRENGTH AT 2% ELONGATION</b>	MO 302/63	KN/m	L : > 40 - 20 % T : > 40 - 20 %
<b>ELONGATION AT BREAK</b>	MO 302/63	%	L : < 3 + 0,5% T : < 3 + 0,5%
<b>THICKNESS (indicative value)</b>	MO P2000HA-D05	mm	1,1