

ROADTEX™ RL100X100 E60A

Issued : 15.10.09

Revision : 04 from 08.03.18

CONSTRUCTION :		WEIGHT / SQM
Warp	: 0.25 End / cm x 1 x 1200 tex Glass 2 x 2400 tex Glass	300
Scrim		
Weft	: 0.25 End / cm x 2 x 2400 tex Glass 2 x 600 tex Glass	
Coating	SBR	90
Tissue	Polyester	60
TOTAL WEIGHT (MO P2000HA-D05)		450 ± 10 %

PROPERTIES : according to ISO 10319			L : length direction T : cross direction
TENSILE STRENGTH	MO 302/63	KN/m	L : > 100 - 5% T : > 100 - 5%
TENSILE STRENGTH AT 1% ELONGATION	MO 302/63	KN/m	L : > 32 - 5% T : > 32 - 5%
TENSILE STRENGTH AT 2% ELONGATION	MO 302/63	KN/m	L : > 66 - 5% T : > 66 - 5%
ELONGATION AT BREAK	MO 302/63	%	L : < 3 + 0,5% T : < 3 + 0,5%
THICKNESS (indicative value)	MO P2000HA-D05	mm	1,6