

## ROADTEX™ RL 50X50 E60A

Issued : 11.05.10

Revision : 04 from 08.03.18

CONSTRUCTION :		WEIGHT / SQM
Warp	: 0.25 End / cm x 1 x 1200 tex Glass 1 x 2400 tex Glass	<b>158</b>
Scrim		
Weft	: 0.25 End / cm x 1 x 2400 tex Glass 1 x 320 tex Glass	
Coating	SBR	<b>53</b>
Tissue	Polyester	<b>60</b>
<b>TOTAL WEIGHT (MO P2000HA-D05)</b>		<b>271 ± 10 %</b>

PROPERTIES : according to ISO 10319		L : length direction T : cross direction
<b>TENSILE STRENGTH</b>	MO 302/63 KN/m	L : > 50 - 5% T : > 50 - 5%
<b>TENSILE STRENGTH AT 1% ELONGATION</b>	MO 302/63 KN/m	L : > 18 - 5% T : > 15 - 5%
<b>TENSILE STRENGTH AT 2% ELONGATION</b>	MO 302/63 KN/m	L : > 38 - 5% T : > 32 - 5%
<b>ELONGATION AT BREAK</b>	MO 302/63 %	L : < 3 + 0,5% T : < 3 + 0,5%
<b>THICKNESS (indicative value)</b>	MO P2000HA-D05 mm	1,3