

ROTATEX™ GE600 E100A

Issued : 07.07.08

Revision : 02 from 09.02.10

CONSTRUCTION : Allowance : $\pm 10\%$		WEIGHT / SQM
Scrim	Warp : 3 Ends / cm x 3 x 68 tex Glass 1 x 110 tex Polyester Weft : 3.3 Ends / cm x 3 x 68 tex Glass 1 x 110 tex Polyester	49
Coating	SB Type	26
Tissue	PET	100
TOTAL WEIGHT (Procedure NR 302/03)		175

PROPERTIES : minimum values			L : length direction T : cross direction
TENSILE STRENGTH	MO 302/13	N/5 cm	L :600 (at 3% all) T :600(at 3% all)
ELONGATION AT BREAK	MO 302/13	%	L : 17 T : 17

THICKNESS (indicative value)	MO 302/03	mm	0,70
-------------------------------------	-----------	----	------