

ROTATEX™ G500 E60B

Issued : 31.01.11

Revision : 01 from 16.05.11

CONSTRUCTION : Tolérances : $\pm 10\%$		WEIGHT / SQM
Warp : 2 Ends / cm x 68 tex Glass		27
Scrim Weft : 2 Ends / cm x 68 tex Glass		
Coating Latex Type		18
Tissue Polyester		60
TOTAL WEIGHT (MO 302/03)		105

PROPERTIES : minimum values		L : length direction T : cross direction	
TENSILE STRENGTH	MO 302/13 N/5 cm	L : 500	T : 500
ELONGATION AT BREAK	MO 302/13 %	L : <4,5 +0,5	T : <4,5 +0,5

THICKNESS (indicative value)	MO 302/03 mm	0,6
-------------------------------------	--------------	-----